

Description

ST 20K FS 5W-30 DXS 6/1Q

Inspection Information	Test Method	Typical Value
Gravity, °API	ASTM D287	35.03
Specific Gravity at 60°F (15.6°C)	ASTM D4052	0.8497
Flash Point, °C	ASTM D92	233
Flash Point, °F	ASTM D92	451
Viscosity at 40°C, cSt	ASTM D445	58.44
Viscosity at 100°C, cSt	ASTM D445	10.37
Viscosity Index	ASTM D2270	168
Pour Point, °C (°F)	ASTM D5950	-42°C (-44°F)
Cold Cranking Simulator at (°C), cP	ASTM D5293	4200 (-30)
High Temperature / High Shear Vis at 150°C, cP	ASTM D5481	3.1
Noack Volatility, % loss	ASTM D5800	11.6
Color	ASTM D1500	3
Zinc, wt. %	ASTM D5185	0.082
Phosphorus, wt. %	ASTM D5185	0.074
Calcium, wt. %	ASTM D5185	0.101
Sulfur, wt. %	ASTM D4951	0.226
Magnesium, wt. %	ASTM D5185	0.056
Boron, wt. %	ASTM D5185	0.14
Molybdenum, wt. %	ASTM D5185	0.004
Sulfated Ash, wt. %	ASTM D874	0.7
Nitrogen, wt. %	ASTM D4629	0.114
Pumping Viscosity at (°C), cP	ASTM D4684	17,100 (-35)
Shear Stability, Final Viscosity in cSt	ASTM D6278	9.4
Foam Seq. I (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. II (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. III (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
High Temperature Foaming, static foam	ASTM D6082 (Opt A)	20/0
TBN, mgKOH/g	ASTM D2896	8



Claims Information

API SJ, SH, SG, SF, SE, SD, SC	Recommended For
API SL	Recommended For
API SM	Recommended For
API SN	Recommended For
API SN PLUS	Recommended For
API SP	Approved
Chrysler MS-6395	Recommended For
dexos1 gen 3	Approvable by Brand
Ford WSS M2C946-B1, M2C946-A M2C929-A	Recommended For
Ford WSS M2C961-A1	Recommended For
GM 4718M	Recommended For
GM 6094M	Recommended For
ILSAC GF-4, GF-3, GF-2, GF-1	Recommended For
ILSAC GF-5	Recommended For
ILSAC GF-6A	Approved

